Fig. 1


FIRING SCHEDULE
— FIRST COATING
--- SECOND COATING
COOLING CYCLE
(IN FURNACE)
2 HOUR ANNEAL
1150°
1350°
TEMPERATURE (°C)
1400
1200
1000
800
600
400
200
R.T.
0
1
2
3
4
5
6
7
8
TIME (HOURS)