



US009408503B2

(12) **United States Patent**  
**Manifold et al.**

(10) **Patent No.:** **US 9,408,503 B2**

(45) **Date of Patent:** **\*Aug. 9, 2016**

(54) **FIBROUS STRUCTURES**  
(71) Applicant: **The Procter & Gamble Company**,  
Cincinnati, OH (US)  
(72) Inventors: **John Allen Manifold**, Sunman, IN (US);  
**Joshua Thomas Fung**, Cincinnati, OH  
(US); **Jeremy Howard Nugent**, Liberty  
Township, OH (US); **Ashley Lynn**  
**Kuntz**, Cincinnati, OH (US); **Katie**  
**Kristine Fleming Glass**, Maineville, OH  
(US); **Kathryn Christian Kien**,  
Cincinnati, OH (US); **Kevin Mitchell**,  
West Chester, OH (US)

(73) Assignee: **The Procter & Gamble Company**,  
Cincinnati, OH (US)  
(\* ) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/016,355**

(22) Filed: **Sep. 3, 2013**

(65) **Prior Publication Data**

US 2014/0000826 A1 Jan. 2, 2014

**Related U.S. Application Data**

(63) Continuation of application No. 13/677,925, filed on  
Nov. 15, 2012, now Pat. No. 8,545,976, which is a  
continuation of application No. 12/700,261, filed on  
Feb. 4, 2010, now Pat. No. 8,334,050.

(51) **Int. Cl.**  
**D21H 27/30** (2006.01)  
**A47K 10/16** (2006.01)  
**D21H 27/00** (2006.01)

(52) **U.S. Cl.**  
CPC ..... **A47K 10/16** (2013.01); **D21H 27/002**  
(2013.01); **D21H 27/005** (2013.01); **D21H**  
**27/30** (2013.01);

(Continued)

(58) **Field of Classification Search**  
USPC ..... 162/112, 135, 109, 123, 231; 428/113,  
428/326  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,952,260 A 9/1960 Burgeni  
3,737,368 A 6/1973 Such et al.

(Continued)

FOREIGN PATENT DOCUMENTS

EP 0 677 612 10/1995  
EP 1 876 291 A2 1/2005

(Continued)

OTHER PUBLICATIONS

All Office Action in U.S. Appl. No. 13/420,983, U.S. Appl. No.  
12/040,662, U.S. Appl. No. 12/814,851, U.S. Appl. No. 13/899,706,  
U.S. Appl. No. 13/098,746, U.S. Appl. No. 13/938,519, U.S. Appl.  
No. 12/040,715, U.S. Appl. No. 13/463,152, U.S. Appl. No.  
13/078,275, U.S. Appl. No. 13/927,499, U.S. Appl. No. 13/677,816,  
U.S. Appl. No. 13/677,925, U.S. Appl. No. 12/913,413.

(Continued)

*Primary Examiner* — Jacob Thomas Minsky  
(74) *Attorney, Agent, or Firm* — C. Brant Cook

(57) **ABSTRACT**

Fibrous structures that exhibit a Geometric Mean Modulus  
(GM Modulus) of less than 1402.4 g/cm at 15 g/cm as mea-  
sured according to the Modulus Test Method described herein  
and a Geometric Mean Elongation (GM Elongation or GM  
Elong) of less than 10.2% measured according to the Elong-  
ation Test Method described herein are provided.

**12 Claims, 8 Drawing Sheets**

