United States Patent [19]

Shimizu et al.

[11] **Patent Number: 5,049,613**

[45] **Date of Patent: Sep. 17, 1991**

[54] **THERMOPLASTIC RESIN COMPOSITION**

[75] Inventors: **Sachio Shimizu**, Chiba; **Tetsuji Miura**, Tokyo; **Toshio Noda**, Ichihara; **Hiroshi Murakami**, Isesaki, all of Japan

[73] Assignee: **Denki Kagaku Kogyo Kabushiki Kaisha**, Tokyo, Japan

[21] Appl. No.: **310,903**

[22] Filed: **Feb. 16, 1989**

[30] **Foreign Application Priority Data**

Feb. 24, 1988 [JP] Japan 63-41015
Nov. 11, 1988 [JP] Japan 63-283720

[51] **Int. Cl.**[5] **C08L 77/00**
[52] **U.S. Cl.** **525/66**; 525/179
[58] **Field of Search** 525/179, 66

[56] **References Cited**

U.S. PATENT DOCUMENTS

4,174,358 11/1979 Epstein 525/183
4,528,326 7/1985 Dean et al. 525/66
4,543,392 9/1985 Kasahara et al. 525/90
4,740,552 4/1988 Grant et al. 525/66

FOREIGN PATENT DOCUMENTS

0046040 7/1981 European Pat. Off. .
57-57719 4/1982 Japan .
58-71952 4/1983 Japan 525/179
61-171751 8/1986 Japan .
62-22844 1/1987 Japan .
62-59647 3/1987 Japan .
62-161853 4/1987 Japan .
62-179546 8/1987 Japan .
62-185725 8/1987 Japan .
63-017949 1/1988 Japan .
63-105051 5/1988 Japan .
63-193947 8/1988 Japan .
63-193955 8/1988 Japan .

OTHER PUBLICATIONS

Patent Abstracts of Japan, vol. 12, No. 5 (C-467) [2852], Jan. 8, 1988; & JP-A-62 161 853 (Denki Kagaku Kogyo K.K.) 17-07-1987.

Chemical Abstracts, vol. 108, Feb. 22, 1988, p. 37, Abstract No. 57163h, Columbus, Ohio, U.S.; & JP-A-62 179 546 (Japan Synthetic Rubber Co., Ltd) 06-08-1987.

Primary Examiner—Ana L. Carrillo
Attorney, Agent, or Firm—Oblon, Spivak, McClelland, Maier & Neustadt

[57] **ABSTRACT**

A thermoplastic resin composition comprising:

(A) from 10 to 50% by weight of a maleimide copolymer of from 30 to 70 mol % of an aromatic vinyl monomer, from 30 to 50 mol % of a maleimide monomer, from 3 to 20 mol % of an unsaturated dicarboxylic anhydride monomer and from 0 to 50 mol % of other copolymerizable monomer;

(B) from 40 to 80% by weight of a polyamide; and

(C) from 3 to 40% by weight of a polyolefin polymer modified by from 0.1 to 10% by weight of an unsaturated dicarboxylic anhydride monomer and/or an unsaturated carboxylic acid monomer,

wherein said maleimide copolymer is in the form of dispersed particles of from 0.01 to 1.0 μm.

8 Claims, 2 Drawing Sheets