US007847115B2

(12) **United States Patent**
Schubert et al.

(10) **Patent No.: US 7,847,115 B2**
(45) **Date of Patent: Dec. 7, 2010**

(54) **PROCESS FOR PREPARING POROUS ORGANIC FRAMEWORK MATERIALS**

(75) Inventors: **Markus Schubert**, Ludwigshafen (DE); **Ulrich Mueller**, Neustadt (DE); **Hendrick Mattenheimer**, Ludwigshafen (DE)

(73) Assignee: **BASF Aktiengesellschaft**, Ludwigshafen (DE)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 271 days.

(21) Appl. No.: **12/161,024**

(22) PCT Filed: **Feb. 8, 2007**

(86) PCT No.: **PCT/EP2007/051211**

§ 371 (c)(1),
(2), (4) Date: **Jul. 16, 2008**

(87) PCT Pub. No.: **WO2007/090864**

PCT Pub. Date: **Aug. 16, 2007**

(65) **Prior Publication Data**

US 2010/0160661 A1 Jun. 24, 2010

(51) **Int. Cl.**
C07F 3/00 (2006.01)
C07F 15/00 (2006.01)
C07F 5/02 (2006.01)

(52) **U.S. Cl.** **556/132**; 556/115; 556/147; 568/3; 568/6

(58) **Field of Classification Search** 556/115, 556/132, 147; 568/3, 6
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,648,508 A 7/1997 Yaghi

FOREIGN PATENT DOCUMENTS

DE 101 11 230 9/2002
EP 0 790 253 8/1997
WO 02 070526 9/2002
WO 02 088148 11/2002
WO 03 102000 12/2003

OTHER PUBLICATIONS

U.S. Appl. No. 12/668,436, filed Jan. 11, 2010, Schubert, et al.
U.S. Appl. No. 12/594,604, filed Oct. 5, 2009, Stein, et al.
U.S. Appl. No. 12/597,616, filed Oct. 26, 2009, Schubert, et al.
U.S. Appl. No. 12/601,022, filed Nov. 20, 2009, Schubert, et al.
U.S. Appl. No. 12/600,539, filed Nov. 17, 2009, Schubert, et al.
O'Keeffe, M. et al., "Frameworks for Extended Solids: Geometrical Design Principles", Journal of Solid State Chemistry, vol. 152, pp. 3-20, (2000).
Eddaoudi, Mohamed et al., "Design and synthesis of metal-carboxylate frameworks with permanent microporosity", Topics in Catalysis, vol. 9, pp. 105-111, (1999).
Sudik, Andrea C. et al., "Design, Synthesis, Structure, and Gas (N2, Ar, CO2, CH4, and H2) Sorption Properties of Porous Metal-organic Tetrahedral and Heterocuboidal Polyhedra", J. Am. Chem. Soc., vol. 127, pp. 7110-7118, (2005).
Rowsell, Jesse L. C. et al., "Hydrogen Sorption in Functionalized Metal-Organic Frameworks", J. Am. Chem. Soc., vol. 126, pp. 5666-5667, (2004).
Li, Haillan et al., "Design and synthesis of an exceptionally stable and highly porous metal-organic framework", Nature, vol. 402, pp. 276-279, (1999).
Chen, Banglin et al., "Interwoven Metal-Organic Framework on a Periodic Minimal Surface with Extra-Large Pores", Science, vol. 291, pp. 936-937 and 1021-1023, (2001).
Cote, Adrien P. et al., "Porous, Crystalline, Covalent Organic Frameworks", Science, vol. 310, pp. 1116-1170, (2005).

Primary Examiner—Porfirio Nazario Gonzalez
(74) *Attorney, Agent, or Firm*—Oblon, Spivak, McClelland, Maier & Neustadt, L.L.P.

(57) **ABSTRACT**

The present invention relates to a process for preparing porous organic frameworks by reaction of a reaction mixture in a liquid phase comprising the appropriate starting compounds in the presence of a nonaqueous organic solvent in the presence of and/or with liberation of water, wherein the latter is withdrawn from the liquid phase of the reaction mixture during the reaction. Here, frameworks having relatively high specific surface areas can be obtained in a reproducible way.

10 Claims, No Drawings