106-90. AU 115 EX
12-2-75 XR 3,923,717

United States Patent [19]

Lalk et al.

[11] **3,923,717**

[45] **Dec. 2, 1975**

[54] **A KILN FEED SLURRY FOR MAKING PORTLAND CEMENT CONTAINING AN INORGANIC SLAT OF A STYRENE-MALEIC ANHYDRIDE COPOLYMER**

[75] Inventors: **Robert H. Lalk; Syamalarao Evani,** both of Midland, Mich.

[73] Assignee: **The Dow Chemical Company,** Midland, Mich.

[22] Filed: **Aug. 19, 1974**

[21] Appl. No.: **498,482**

[52] **U.S. Cl.** ..... **260/29.6 S;** 106/90; 106/314; 260/29.6 H; 260/42.13

[51] **Int. Cl.**[2] **C08K 3/00;** C04B 7/02; C04B 7/35

[58] **Field of Search** ..... 260/29.6 S, 29.6 H, 42.13; 106/90, 314

[56] **References Cited**

UNITED STATES PATENTS

2,614,998	9/1949	Lea	260/29.6 S
3,037,957	6/1962	Bruere	260/29.6 S
3,140,269	7/1964	Wahl et al.	260/29.6 S
3,563,777	2/1971	Pratt et al.	260/29.6 S
3,563,930	2/1971	Stram et al.	260/29.6 S

Primary Examiner—Eugene C. Rzucidlo
Attorney, Agent, or Firm—Stephen Hoynak

[57] **ABSTRACT**

Superior reduction of water demand of wet process portland cement slurries is shown by water-soluble salts of styrene-maleic anhydride copolymers, having a molecular weight range of from about 1000 to about 5000.

12 Claims, No Drawings