

11

11. The composition of claim 9 wherein the average molecular weight of the non-reactive siloxane polymer is about 1900 to about 100,000.

12. The composition of claim 1 wherein there is additionally incorporated a solution of a metallic catalyst. 5


13. The composition in accordance with claim 1 wherein the first siloxane polymer of structure I has a molecular weight of about 5,000 to 25,000;

the first siloxane polymer of structure II has a molecular weight of about 30,000 to 75,000; and 10

the non-reactive lubricating siloxane polymer has a molecular weight between 5,000 and 100,000.

14. A process for producing a film having in combination lubricating and adhering properties characterized by the steps of 15

(a) admixing in a first admixing step a first siloxane polymer, a siloxane cross-linking polymer and a siloxane chain-extending polymer, said first siloxane polymer having the formula selected from the group consisting of 20




and




wherein R is selected from the group consisting of alkyl C<sub>1-20</sub>, haloalkyl, aryl, haloaryl, cycloalkyl, silacyclopentyl, aralkyl and mixtures thereof; x is 25

12

about 60 to about 1000; and y is about 3 to about 25; and said siloxane cross-linking polymer having the formula




wherein x is about 8 to about 12 and said siloxane chain extending polymer having the formula



wherein x is about 140 to about 160;

(b) admixing in a second admixing step the admixture from said first admixing step with a non-reactive lubricating siloxane polymer of the formula 20



wherein R is selected from the group consisting of alkyl C<sub>1-20</sub>, haloalkyl, aryl, haloaryl, cycloalkyl, silacyclopentyl, aralkyl, and mixtures thereof; x is about 20 to about 1350; and

(c) the mole ratio of vinyl groups to hydrogen groups is within the range of between about 0.010:1 and 0.2:1; and

(d) curing the admixture derived from said second admixing step. 35

\* \* \* \* \*

40

45

50

55

60

65