United States Patent [19]

Clark et al.

[11] **Patent Number: 4,985,525**

[45] **Date of Patent: Jan. 15, 1991**

[54] **CLEAR ORGANOSILOXANE COMPOSITIONS**

[75] Inventors: **Joseph N. Clark**, Mapleton; **Schuyler B. Smith**, Midland, both of Mich.

[73] Assignee: **Dow Corning Corporation**, Midland, Mich.

[21] Appl. No.: **322,014**

[22] Filed: **Mar. 13, 1989**

[51] **Int. Cl.**[5] **C08G 77/12**; C08G 77/16

[52] **U.S. Cl.** **528/15**; 528/31; 528/32; 525/478

[58] **Field of Search** 525/478; 528/15, 31, 528/32

[56] **References Cited**

U.S. PATENT DOCUMENTS

3,677,981	7/1972	Wada et al.	528/32
3,817,910	6/1974	Viksne	528/32
4,045,390	8/1977	Itoh et al.	528/15
4,719,262	1/1988	Plueddmann	525/105
4,732,931	3/1988	Maxson	524/862
4,795,775	1/1989	Baile et al.	524/379
4,857,564	8/1989	Maxson	523/212

Primary Examiner—John C. Bleutge
Assistant Examiner—R. Dean, Jr.
Attorney, Agent, or Firm—Robert Spector

[57] **ABSTRACT**

The degree and reproducibility of cohesive bonding between gum-type organosiloxane elastomers cured by a platinum-catalyzed hydrosilation reaction and organic polymer substrates are increased when the composition used to prepare the elastomer contains an amount of silanol-functional polydirganosiloxane sufficient to impart an activity number of at least 40 to the polydiorganousiloxane gums present in said composition.

3 Claims, No Drawings