and prevent the beam, along with the molten metal and debris from the cut, from impinging on the opposite surface of the tube.

In addition to the laser and the CNC positioning equipment, the optical delivery system includes a beam expander to increase the laser beam diameter, a circular polarizer, typically in the form of a quarter wave plate, to eliminate polarization effects in metal cutting, provisions for a spatial filter, a binocular viewing head and focusing lens, and a coaxial gas jet that provides for the introduction of a gas stream that surrounds the focused beam and is directed along the beam axis. The coaxial gas jet nozzle (0.018" ID.) is centered around the focused beam with approximately 0.010" between the tip of the nozzle and the tubing. The jet is pressurized with oxygen at 20 psi and is directed at the tube with the focused laser beam exiting the tip of the nozzle (0.018" dia.). The oxygen reacts with the metal to assist in the cutting process very similar to oxyacetylene cutting. The focused laser beam acts as an ignition source and controls the reaction of the oxygen with the metal. In this manner, it is possible to cut the material with a very fine kerf with precision. In order to prevent burning by the beam and/or molten slag on the far wall of the tube I.D., a stainless steel mandrel (approx. 0.034" dia.) is placed inside the tube and is allowed to roll on the bottom of the tube as the pattern is cut. This acts as a beam/debris block protecting the far wall I.D.

Alternatively, this may be accomplished by inserting a second tube inside the stent tube which has an opening to trap the excess energy in the beam which is transmitted through the kerf along which collecting the debris that is ejected from the laser cut kerf. A vacuum or positive pressure can be placed in this shielding tube to remove the collection of debris.

Another technique that could be utilized to remove the debris from the kerf and cool the surrounding material would be to use the inner beam blocking tube as an internal gas jet. By sealing one end of the tube and making a small hole in the side and placing it directly under the focused laser beam, gas pressure could be applied creating a small jet that would force the debris out of the laser cut kerf from the inside out. This would eliminate any debris from forming or collecting on the inside of the stent structure. It would place all the debris on the outside. With the use of special protective coatings, the resultant debris can be easily removed.

In most cases, the gas utilized in the jets may be reactive or non-reactive (inert). In the case of reactive gas, oxygen or compressed air is used. Compressed air is used in this application since it offers more control of the material removed and reduces the thermal effects of the material itself. Inert gas such as argon, helium, or nitrogen can be used to eliminate any oxidation of the cut material. The result is a cut edge with no oxidation, but there is usually a tail of molten material that collects along the exit side of the gas jet that must be mechanically or chemically removed after the cutting operation.

The cutting process utilizing oxygen with the finely focused green beam results in a very narrow kerf (approx. 0.0005") with the molten slag re-solidifying along the cut. This traps the cut out scrap of the pattern requiring further processing. In order to remove the slag debris from the cut allowing the scrap to be removed from the remaining stent pattern, it is necessary to soak the cut tube in a solution of HCL for approximately 8 minutes at a temperature of approximately 55° C. Before it is soaked, the tube is placed in a bath of alcohol/water solution and ultrasonically cleaned for approximately 1 minute to remove the loose debris left from the cutting operation. After soaking, the tube is then ultrasonically cleaned in the heated HCL for 1-4 minutes depending upon the wall thickness. To prevent cracking/breaking of the struts attached to the material left at the two ends of the stent pattern due to harmonic oscillations induced by the ultrasonic cleaner, a mandrel is placed down the center of the tube during the cleaning/scrap removal process. At completion of this process, the stent structure are rinsed in water. They are now ready for electropolishing.

The stents are preferably electrochemically polished in an acidic aqueous solution such as a solution of ELECTRO-GLO#300, sold by ELECTRO-GLO Co., Inc. in Chicago, Ill., which is a mixture of sulfuric acid, carboxylic acids, phosphates, corrosion inhibitors and a biodegradable surface active agent. The bath temperature is maintained at about 110°-1350° F. and the current density is about 0.4 to about 1.5 amps per in.$^2$. Cathode to anode area should be at least about two to one. The stents may be further treated if desired, for example by applying a biocompatible coating.

It will be apparent that both focused laser spot size and depth of focus can be controlled by selecting beam diameter and focal length for the focusing lens. It will be apparent that increasing laser beam diameter, or reducing lens focal length, reduces spot size at the cost of depth of field.

Direct laser cutting produces edges which are essentially perpendicular to the axis of the laser cutting beam, in contrast with chemical etching and the like which produce pattern edges which are angled. Hence, the laser cutting process essentially provides strut cross-sections, from cut-to-cut, which are square or rectangular, rather than trapezoidal. As depicted, cylindrical rings **40** are comprised of struts **98** which have generally rectangular cross-sections **100** when the stent is laser cut from a tubular member. The struts have generally perpendicular edges formed by the laser cut. The resulting stent structure provides superior performance.

Other methods of forming the stent of the present invention can be used, such as chemical etching; electric discharge machining; laser cutting a flat sheet and rolling it into a cylinder; and the like, all of which are well known in the art at this time.

The stent of the present invention also can be made from metal alloys other than stainless steel, such as shape memory alloys. Shape memory alloys are well known and include, but are not limited to, nickel titanium and nickel/titanium/vanadium. Any of the shape memory alloys can be formed into a tube and laser cut in order to form the pattern of the stent of the present invention. As is well known, the shape memory alloys of the stent of the present invention can include the type known as thermoelastic martensitic transformation, or display stress-induced martensite. These types of alloys are well known in the art and need not be further described here.

Importantly, a stent formed of shape memory alloys, whether the thermoelastic or the stress-induced martensite-type, can be delivered using a balloon catheter of the type described herein, or in the case of stress induced martensite, be delivered via a catheter without a balloon or a sheath catheter.

While the invention has been illustrated and described herein, in terms of its use as an intravascular stent, it will be apparent to those skilled in the art that the stent can be used in other body lumens. Further, particular sizes and dimensions, number of crowns per ring, materials used, and the like have been described herein and are provided as examples only. Other modifications and improvements may be made without departing from the scope of the invention.

What is claimed:

**1**. A method of expanding a longitudinally flexible stent without stent shortening, comprising:

providing a plurality of cylindrical rings, each cylindrical ring being connected to an adjacent cylindrical ring by