United States Patent [19]

Chiang

[11] **4,126,528**

[45] **Nov. 21, 1978**

[54] **ELECTROPHORETIC COMPOSITION AND DISPLAY DEVICE**

[75] Inventor: **Anne Chiang**, Santa Clara, Calif.

[73] Assignee: **Xerox Corporation**, Stamford, Conn.

[21] Appl. No.: **819,076**

[22] Filed: **Jul. 26, 1977**

[51] **Int. Cl.**[2] **C25D 1/12**; G03G 13/00

[52] **U.S. Cl.** ..... **204/180 R**; 204/181 R; 204/299 R; 204/300 R; 96/1 A; 252/62.1 L; 252/300; 350/363

[58] **Field of Search** ..... 204/181 PE, 180 R, 299 PE, 204/299 R, 300 PE; 350/160 R, 363; 96/1 A; 355/3 R; 357/73, 60

[56] **References Cited**

U.S. PATENT DOCUMENTS

3,668,106	6/1972	Ota	204/299 PE
3,689,399	9/1972	Ota	204/181 PE X
3,756,693	9/1973	Ota	204/181 PE X
3,812,406	5/1974	Henri	357/73
3,914,040	10/1975	McVeigh	355/3

Primary Examiner—Arthur C. Prescott

[57] **ABSTRACT**

Electrophoretic display device containing a suspension of hollow particles in an insulating medium, wherein the weight density of the particles is equal to, or within five percent of, that of the insulating medium. Settling out of the particles is, thus, greatly reduced or eliminated during periods of non-use.

8 Claims, No Drawings