US009410033B2

(12) **United States Patent**
Kagawa et al.

(10) **Patent No.: US 9,410,033 B2**
(45) **Date of Patent: Aug. 9, 2016**

(54) **RUBBER COMPOSITION FOR UNDERTREAD, AND PNEUMATIC TIRE**

(71) Applicant: **SUMITOMO RUBBER INDUSTRIES, LTD.**, Kobe-shi, Hyogo (JP)

(72) Inventors: **Yoshihiro Kagawa**, Kobe (JP); **Naoya Ichikawa**, Kobe (JP)

(73) Assignee: **SUMITOMO RUBBER INDUSTRIES, LTD.**, Kobe-Shi (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/483,966**

(22) Filed: **Sep. 11, 2014**

(65) **Prior Publication Data**

US 2014/0378593 A1 Dec. 25, 2014

Related U.S. Application Data

(62) Division of application No. 13/672,880, filed on Nov. 9, 2012, now abandoned.

(30) **Foreign Application Priority Data**

Nov. 11, 2011 (JP) 2011-247879

(51) **Int. Cl.**

C08L 65/02	(2006.01)
C08L 7/02	(2006.01)
C08L 15/00	(2006.01)
C08K 3/00	(2006.01)
B60C 1/00	(2006.01)
C08C 1/04	(2006.01)

(52) **U.S. Cl.**

CPC ***C08L 7/02*** (2013.01); ***B60C 1/0016*** (2013.04); ***C08K 3/0033*** (2013.01); ***C08L 15/00*** (2013.01); ***C08L 65/02*** (2013.01); *C08C 1/04* (2013.01); *Y02T 10/862* (2013.01)

(58) **Field of Classification Search**

None

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,140,527	A		12/1938	Haynes et al.
2,486,720	A		11/1949	Perkerson
2,650,891	A		9/1953	Buckwalter
2,905,567	A		9/1959	Allen
3,709,845	A		1/1973	Boustany et al.
3,716,513	A		2/1973	Burke, Jr.
3,959,194	A		5/1976	Adelmann
4,508,860	A		4/1985	Hawes
4,835,216	A		5/1989	Morikawa et al.
5,000,092	A		3/1991	Best
5,017,636	A		5/1991	Hattori et al.
5,290,830	A		3/1994	Tung et al.
5,396,940	A		3/1995	Segatta et al.
5,569,740	A		10/1996	Tanaka et al.
5,908,893	A	*	6/1999	Kawasaki et al. 524/575.5
5,967,211	A		10/1999	Lucas et al.
6,117,545	A		9/2000	Cavaille et al.
6,306,955	B1		10/2001	Kawasaki et al.
6,376,587	B1		4/2002	Ajiro et al.
6,489,389	B1		12/2002	Ohta et al.
6,703,497	B1		3/2004	Ladouce et al.
7,427,646	B2		9/2008	Kondou
8,022,136	B2		9/2011	Yano et al.
8,163,821	B2		4/2012	Hiro
8,273,804	B2		9/2012	Nishimura
8,623,956	B2		1/2014	Sugimoto et al.
8,633,275	B2		1/2014	Sakaki et al.
8,658,728	B2		2/2014	Ichikawa et al.
8,658,730	B2		2/2014	Ichikawa
8,809,450	B2		8/2014	Sakaki et al.
8,813,798	B2		8/2014	Tsumori et al.
8,857,482	B2		10/2014	Taguchi et al.
8,875,765	B2		11/2014	Tsumori et al.
2003/0060551	A1		3/2003	Mizuno et al.
2003/0083516	A1		5/2003	Korth et al.
2004/0110889	A1		6/2004	Yagi et al.
2004/0266937	A1		12/2004	Yagi et al.
2005/0027060	A1		2/2005	Yagi et al.
2005/0148723	A1		7/2005	Kondou
2005/0234186	A1		10/2005	Kondou

(Continued)

FOREIGN PATENT DOCUMENTS

CN	1572825 A	2/2005
CN	1692128 A	11/2005

(Continued)

OTHER PUBLICATIONS

"Shinpan Kobunshi Jiten" (Polymer Dictionary, New Edition), 6th Imp., published Mar. 20, 2001, p. 448, with partial translation of lines 21-30 of the left column of p. 448 (3 pages total).

Extended European Search Report, dated Aug. 27, 2010, for European Application No. 08830800.2.

Food Chemicals Codex, 7th Edition, Calcium Lignosulfonate, p. 142, 2010.

The Chemical Society of Japan, "Hyojun Kagaku Yogo Jiten" (Standard Dictionary of Chemical Terms), 2nd Ed., published Mar. 31, 2005, pp. 672-673, with partial translation of lines 5-9 of the left column of p. 673 (3 pages total).

Tokai Carbon Co., Ltd., "SEAST SO (FEF)", Physicochemical Properties, Product Information, retrieved Feb. 20, 2014, 3 pages, http://www.tokaicarbon.co.jp/en/products/carbon_b/seast/.

U.S. Notice of Allowance for U.S. Appl. No. 13/350,407, dated Apr. 23, 2014.

(Continued)

Primary Examiner — Nicole M Buie-Hatcher
Assistant Examiner — Chelsea M Christensen
(74) *Attorney, Agent, or Firm* — Birch, Stewart, Kolasch & Birch, LLP

(57) **ABSTRACT**

The present invention provides a rubber composition for an undertread, which has improved in processability, fuel economy, and tensile properties in a balanced manner, and also provides a pneumatic tire formed from the rubber composition. The present invention relates to a rubber composition for an undertread, including: a rubber component containing a modified natural rubber having a phosphorus content of 200 ppm or less; and carbon black and/or a white filler, wherein the modified natural rubber is contained in an amount of 5% by mass or more per 100% by mass of the rubber component.

2 Claims, No Drawings