

4. The adhesive of claim 1, wherein said polyol component has an equivalent weight (average) of 100-5,000 and a functionality (average) of 2-8.

5. The adhesive of claim 1, wherein said polyisocyanate is at least one selected from the group consisting of aromatic polyisocyanates containing 6-20 carbon atoms, aliphatic polyisocyanates containing 2-18 carbon atoms, alicyclic polyisocyanates containing 4-15 carbon atoms, araliphatic polyisocyanates containing 8-15 carbon atoms, except carbon atoms in NCO groups, and modified polyisocyanates of these polyisocyanates containing one or more of urethane, carbodiimide, allophanate, urea, biuret, urethdione, urethimine, isocyanurate and oxazolidone groups.

6. The adhesive of claim 1, wherein said polyisocyanate is p-phenylene diisocyanate, or a combination thereof with one or more other polyisocyanates.

7. The adhesive of claim 1, wherein said hydrophilic polyether polyol is at least one adduct of ethylene oxide or a combination thereof with one or more other alkylene oxides to at least one compound containing two or more active hydrogen atoms.

8. The adhesive of claim 7, wherein said compound containing two or more active hydrogen atoms is at least one selected from the group consisting of polyhydric alcohols, polyhydric phenols, amines, polycarboxylic acids and phosphorous acids.

9. The adhesive of claim 1, wherein said hydrophilic polyether polyol is at least one selected from the group consisting of polyoxyethylene polyols, polyoxy-

ethylene/oxypropylene polyols and polyoxyethylene/oxybutylene polyols.

10. The adhesive of claim 1, wherein said polyol component comprises said hydrophilic polyether polyol and at least one other polyol selected from the group consisting of low molecular weight polyols, hydrophobic polyether polyols and polyester polyols.

11. The adhesive of claim 1, wherein said prepolymer is obtained by reacting said polyisocyanate with said polyol component in such an amount providing NCO-/OH ratio of 1.5-5.0.

12. The adhesive of claim 1, which comprises 20-90% by weight of said prepolymer and 10-80% by weight of said cyano compound.

13. The adhesive of claim 1, wherein said cyano compound is at least one compound selected from the group consisting of cyanoacrylic acid, cyanomethacrylic acid, cyanoacrylates, cyanomethacrylates, acrylonitrile, methacrylonitrile, cyanoacrylonitrile and cyanomethacrylonitrile.

14. The adhesive of claim 1, wherein said cyano compound is at least one cyanoacrylic ester selected from the group consisting of methyl cyanoacrylate, ethyl cyanoacrylate and iso-butyl cyanoacrylate.

15. The adhesive of claim 1, which contains up to 20% by weight of at least one additive selected from the group consisting of carbon black, metal oxides, silicates, acrylic resin powders, ceramic powders, softening agents, and stabilizers.

* * * * *

35

40

45

50

55

60

65