

- [54] METHOD OF MAKING INTRAOCULAR AND CONTACT LENS CONSTRUCTIONS
- [75] Inventor: Stanley Poler, New York, N.Y.
- [73] Assignee: Lynell Medical Technology Inc., New York, N.Y.
- [21] Appl. No.: 508,931
- [22] Filed: Jun. 29, 1983

Related U.S. Application Data

- [62] Division of Ser. No. 319,622, Nov. 9, 1981, Pat. No. 4,450,593.
- [51] Int. Cl.³ B44C 1/22; C03C 15/00; C03C 25/06; B29C 17/08
- [52] U.S. Cl. 156/630; 156/643; 156/645; 156/646; 156/652; 156/661.1; 156/663; 156/668; 430/321
- [58] Field of Search 156/629, 630, 633, 643, 156/645, 646, 650, 652, 655, 659.1, 661.1, 663, 668; 430/313, 316, 317, 321; 351/160 R; 250/492.1

References Cited

U.S. PATENT DOCUMENTS

- 3,959,527 5/1976 Droege 156/650 X
- 4,116,753 9/1978 Tojyo et al. 156/629

Primary Examiner—William A. Powell
Attorney, Agent, or Firm—Hopgood, Calimafde, Kalil, Blaustein & Judlowe

[57] **ABSTRACT**

The invention contemplates effectively integral lens-and-haptic structure and a technique of making the same, using composite laminated sheet material as the only ingredient of the ultimate product, which may be an intraocular implant or for extraocular (i.e., cornea-contact) application. The composite sheet material is of substantially the combined ultimate thickness of the lens and haptic, one of the laminations being of a material destined to be substantially only the lens component, and another of the laminations being of a material destined to be substantially only the haptic component. The lens-component lamination may be of optical-quality glass or of a transparent plastic which is inert to body fluids. Suitably coordinated masking and etching steps determine the contour of the ultimate central circular lens as well as the thickness and fenestration detail of the ultimate thin flexible haptic formations which are integral with and extend radially outward of the lens blank. Lens-surface curvature may be developed by conventional grinding techniques or by die compression, as appropriate.

14 Claims, 13 Drawing Figures

