

13

4. A composition according to claim 1 where the amount of organosiloxane (C) is sufficient to provide from 1.70 to 2.50 silicon-bonded hydrogen atoms per vinyl radical present in (A) and (B).

5. A composition according to claim 4 where the silicon-bonded hydrogen atoms present in (C) represent from 89 to 95% of the silicon-bonded hydrogen atoms present in said composition.

6. A composition according to claim 1 where polyorganosiloxane (D) contains at least 5 silicon-bonded hydrogen atoms per molecule.

7. A composition according to claim 1 where polyorganosiloxane (D) is represented by the formula $R(CH_3)_2SiO[Si(CH_3)_2O]_a[Si(H)(CH_3)O]_bSi(CH_3)_2R$ where R is hydrogen or CH_3 , b is an integer from 3 to 20, inclusive, and the value of a is such that the viscosity of (D) does not exceed 10 Pa·s at 25° C.

8. A composition according to claim 7 where a is from 0 to 10, inclusive, b is from 3 to 10, inclusive, and R is methyl.

9. A composition according to claim 1 where said polydimethylsiloxane (A) exhibits a molecular weight distribution, determined by gel permeation chromatography, such that (a) there is present at least one peak

14

molecular weight (PMW) species in an amount greater than that of adjacent species of higher and lower molecular weight, the molecular weight of said PMW species being within the range of from 68,000 to 135,000, (b) the molecular weight of the lowest molecular weight polymeric species is within the range of from 854 to 3156, (c) the molecular weight of the highest molecular weight species is within the range from 174,000 to 370,000, and (d) the dispersity index has a value greater than 3.8.

10. A composition according to claim 9 where said ingredient (A) consists essentially of two or more polydimethylsiloxanes wherein a first polydimethylsiloxane contains a PMW species within the range of from 70,000 to 90,000 and a second polydimethylsiloxane species contains a PMW species within the range of from 20,000 to 40,000.

11. A composition according to claim 10 where said first polydimethylsiloxane constitutes from 30 to 70% by weight of ingredient (A).

12. A composition according to claim 1 where the concentration of said platinum catalyst (E) is equivalent to from 5 to 50 parts by weight of platinum per million parts by weight of (A).

* * * * *

25

30

35

40

45

50

55

60

65