

9

each of said compositions in an amount of 6 to 11% by weight.

6. The method of claim 5 in which said submicron silica is a silane treated fumed silica.

7. The method of claim 6 in which the monomer content of both of the thixotropic acrylic ester mono-

10

mer compositions is made up of the monomers bisphenol A diglycidyl ether dimethacrylate, bis-phenol A dimethacrylate, and triethylene glycol dimethacrylate.

8. The method of claim 5 in which said amine activator is N,N-di(2-hydroxyethyl)-p-toluidine and said peroxide catalyst is benzoyl peroxide.

\* \* \* \* \*

10

15

20

25

30

35

40

45

50

55

60

65