US009411158B2

(12) **United States Patent**
Minoura et al.

(10) **Patent No.: US 9,411,158 B2**
(45) **Date of Patent: Aug. 9, 2016**

(54) **MOTH-EYE FILM**

(71) Applicant: **Sharp Kabushiki Kaisha**, Osaka-shi, Osaka (JP)

(72) Inventors: **Kiyoshi Minoura**, Osaka (JP); **Akinobu Isurugi**, Osaka (JP); **Tomoko Teranishi**, Osaka (JP); **Eiji Satoh**, Osaka (JP)

(73) Assignee: **SHARP KABUSHIKI KAISHA**, Osaka (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/424,151**

(22) PCT Filed: **Jul. 12, 2013**

(86) PCT No.: **PCT/JP2013/069155**

§ 371 (c)(1),
(2) Date: **Feb. 26, 2015**

(87) PCT Pub. No.: **WO2014/038288**

PCT Pub. Date: **Mar. 13, 2014**

(65) **Prior Publication Data**

US 2015/0226961 A1 Aug. 13, 2015

(30) **Foreign Application Priority Data**

Sep. 5, 2012 (JP) 2012-195554

(51) **Int. Cl.**

G02B 27/00	(2006.01)
G02B 1/04	(2006.01)
E06B 7/12	(2006.01)
G02B 1/118	(2015.01)

(52) **U.S. Cl.**

CPC ***G02B 27/0006*** (2013.01); ***E06B 7/12*** (2013.01); ***G02B 1/04*** (2013.01); ***G02B 1/118*** (2013.01)

(58) **Field of Classification Search**

CPC G02B 27/0006; G02B 1/118; G02B 1/04; E06B 7/12

USPC 359/507, 599, 601, 609; 428/141, 152

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2004/0067339	A1	4/2004	Gandon et al.
2007/0022798	A1	2/2007	Morinaga et al.
2009/0014416	A1	1/2009	Gandon et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN	101223025	A	7/2008
JP	2003089975	A	3/2003

(Continued)

OTHER PUBLICATIONS

International Search Report PCT/ISA/210 for International Application No. PCT/JP2013/069155 Dated Oct. 22, 2013.

Primary Examiner — Frank Font

(74) *Attorney, Agent, or Firm* — Harness, Dickey & Pierce, P.L.C.

(57) **ABSTRACT**

The present invention provides a moth-eye film that is not likely to cause condensation on the surface. A moth-eye film including: a resin composition that, when formed into a flat film, has a contact angle with water of larger than 5° but smaller than 31.3°, the contact angle measured between a surface of the flat film and a droplet of water dropped onto the surface of the flat film, after 100 msec from contact of the droplet and the surface.

7 Claims, 25 Drawing Sheets