



US005880468A

# United States Patent [19]

[11] Patent Number: **5,880,468**

Irwin et al.

[45] Date of Patent: **Mar. 9, 1999**

[54] **SUPERCONDUCTING TRANSITION-EDGE SENSOR**

[75] Inventors: **Kent D. Irwin; John M. Martinis**, both of Boulder, Colo.

[73] Assignee: **The United States of America as represented by the Secretary of Commerce**, Washington, D.C.

[21] Appl. No.: **702,133**

[22] Filed: **Aug. 26, 1996**

[51] Int. Cl.<sup>6</sup> ..... **G01K 7/16; G01K 7/36; G01K 11/30; G01T 7/00**

[52] U.S. Cl. .... **250/336.2; 374/45; 374/176**

[58] Field of Search ..... **250/336.2; 374/45, 374/176; 505/847, 849**

Irwin, K.D. et al. (1992), "Tungsten thin films for use in cryogenic particle detectors," in *Low Temperature Detectors for Neutrinos and Bank Matter IV*, Booth, N. and Salmon, G. (eds.), Editions Frontiers, France, p. 209.

Irwin K.D. (1995), "An application of electrothermal feedback for high resolution cryogenic particle detection," *Appl. Phys. Lett.* 66(15):1998-2000.

Irwin, K.D. et al. (1995), "A Self-Biasing Cryogenic Particle Detector Utilizing Electrothermal Feedback and a Squid Readout," *IEEE Trans. Appl. Superconductivity* 5:2690-2693.

Irwin, K.D. et al. (1995), (Abstract Only), "A Hot Electron Microcalorimeter for X-ray Detection Using a Superconducting Transition Edge Sensor With Electrothermal Feedback," LTD 6—Sixth International Workshop on Low Temperature Detectors, Beatenberg/Interlaken, Switzerland, Aug. 28-Sep. 1, 1995, Abstract No. B024.

(List continued on next page.)

## [56] References Cited

### U.S. PATENT DOCUMENTS

5,090,819	2/1992	Kapitulnik	374/176
5,264,375	11/1993	Bang et al.	.
5,634,718	6/1997	Martinis et al.	374/45 X
5,641,961	6/1997	Irwin et al.	256/336.2

### FOREIGN PATENT DOCUMENTS

2377643	9/1978	France	250/336.2
830149	5/1981	U.S.S.R.	374/176

### OTHER PUBLICATIONS

Claassen, J.H. et al. (1991), "A contactless method for measurement of the critical current density and critical temperature of superconducting films," *Rev. Sci. Instrum.* 62(4):996-1004.

Frank, M. et al. (1996), "High-resolution X-ray detectors with high-speed Squid readout of superconducting tunnel junctions," *Nucl. Instr. Methods Phys. Res. A* 370:41-43.

Friedrich, S. et al. (1996), "Superconducting Nb-Ta-Al-AlOx-Al X-ray detectors with spatial resolution," *Nucl. Instr. Methods Phys. Res. A* 370:44-46.

Hauser, J.J. et al. (1964), "Superconductivity in Cu and Pt by Means of Superimposed Films with Lead," *Phys. Rev.* 136(3A):637-641.

*Primary Examiner*—Edward J. Glick

*Attorney, Agent, or Firm*—Greenlee Winner and Sullivan, P.C.

## [57] ABSTRACT

This invention provides a method and apparatus for particle detection utilizing an Al/normal-metal bilayer transition-edge sensor (TES) coupled with a particle absorber. The TES is maintained in the transition region where its properties are extremely sensitive to temperature. In the detector, the energy of an absorbed particle is converted to heat by the absorber and the transition from the bilayer's superconducting to normal state is used to sense the temperature rise. The transition temperature,  $T_c$ , of the bilayer can be reproducibly controlled as a function of the relative thicknesses and the total thickness of the superconducting and normal-metal layers. The range of available  $T_c$ 's extends from below 50 mK to above 1 K, allowing the detector to be tailored to the application. For x-ray detection the preferred  $T_c$  is about 50-150 mK. The width of the transition edge can be less than 0.1 mK, which allows very high detector sensitivity.

**29 Claims, 7 Drawing Sheets**

