

[54] **PROCESS FOR THE MANUFACTURE OF SCLERO PROTEIN TRANSPLANTS WITH INCREASED BIOLOGICAL STABILITY**

[75] Inventor: **Heinz-Helmut Werner, Melsungen, Fed. Rep. of Germany**

[73] Assignee: **Intermedicat GmbH, Emmenbrucke, Switzerland**

[21] Appl. No.: **290,519**

[22] Filed: **Aug. 6, 1981**

[51] Int. Cl.³ **C07G 7/00; C08H 1/00; C08H 1/06**

[52] U.S. Cl. **260/123.7; 128/DIG. 8**

[58] Field of Search **260/123.7**

[56] **References Cited**

U.S. PATENT DOCUMENTS

2,649,357	8/1953	Happey et al.	260/123.7
2,928,822	3/1960	Johnsen et al.	260/117
3,073,702	1/1963	Keil et al.	260/123.7 X
3,239,420	3/1966	Gonshery et al.	260/123.7 X
3,308,113	3/1967	Johnsen et al.	260/123.7 X
3,475,404	10/1969	Johnsen et al.	260/123.7
4,264,493	4/1981	Battista	260/123.7 X

Primary Examiner—Howard E. Schain
Attorney, Agent, or Firm—Merriam, Marshall & Bicknell

[57] **ABSTRACT**

In a process for the manufacture of sclero protein transplants in which raw sclero protein from humans or animals is watered, treated with H₂O₂, degreased, rinsed, dried and sterilized, the improvement in which the sclero protein, after rinsing and prior to drying, is treated with glycerin or polyethylene glycol.

8 Claims, 1 Drawing Figure