United States Patent [19]

Medford et al.

[11] **Patent Number: 4,988,779**

[45] **Date of Patent: Jan. 29, 1991**

[54] **ADDITION CURED SILICONE PRESSURE SENSITIVE ADHESIVE**

[75] Inventors: **George F. Medford**, Ballston Lake; **Donald S. Johnson**, Scotia, both of N.Y.

[73] Assignee: **General Electric Company**, Waterford, N.Y.

[21] Appl. No.: **339,041**

[22] Filed: **Apr. 17, 1989**

[51] **Int. Cl.**[5] **C08F 283/00**

[52] **U.S. Cl.** **525/478**; 525/479; 524/315; 524/361; 524/284; 524/366; 524/464; 524/588

[58] **Field of Search** 525/478, 479; 524/588, 524/464, 366, 361, 284, 315

[56] **References Cited**

U.S. PATENT DOCUMENTS

2,676,182	4/1954	Daudt et al.	260/448.2
3,159,601	12/1964	Ashby	260/46.5
3,159,662	12/1964	Ashby	260/448.2
3,188,299	6/1965	Chalk	260/46.5
3,188,300	6/1965	Chalk	260/46.5
3,192,181	6/1965	Moore	260/46.5
3,220,970	11/1965	Carlstrom et al.	524/188
3,220,972	11/1965	Lamoreaux	260/46.5
3,284,406	11/1966	Nelson	260/46.5
3,344,111	9/1967	Chalk	260/46.5
3,383,356	5/1968	Nielson	260/46.5
3,445,420	5/1969	Kookootsedes et al.	260/37
3,453,233	7/1969	Flatt	260/46.5
3,453,234	7/1969	Kookootsedes et al.	260/46.5
3,516,946	6/1970	Modic	252/429
3,532,649	10/1970	Smith et al.	260/18
3,627,851	12/1971	Brady	260/825
3,814,730	6/1974	Karstedt	260/46.5
3,983,298	9/1976	Hahn et al.	428/355
4,340,710	7/1982	Brown, Jr.	528/15
4,510,094	4/1985	Drahnak	556/470
4,774,297	9/1988	Murakami et al.	525/478

FOREIGN PATENT DOCUMENTS

972594 10/1964 United Kingdom .

OTHER PUBLICATIONS

European Patent Application (Murakami et al.), 0269454, Date of Publication 06/01/88.

Primary Examiner—Melvyn I. Marquis
Attorney, Agent, or Firm—M. R. Warfield

[57] **ABSTRACT**

Compositions curable to pressure sensitive adhesives are disclosed which comprise from 30 to 50 parts of a vinyl endblocked polydiorganosiloxane fluid having a viscosity from 500 to 10,000 centipoise at 25° C., from 50 to 70 parts of a benzene soluble resin copolymer having

$R_3SiO_{\frac{1}{2}}$ units and $SiO_{4/2}$ units,

an organopolysiloxane having silicon bonded hydrogen atoms for the purpose of curing the composition and developing the PSA properties, and a platinum catalyst for the curing process.

22 Claims, No Drawings