US008628880B2

(12) **United States Patent**
Li et al.

(10) **Patent No.: US 8,628,880 B2**
(45) **Date of Patent: Jan. 14, 2014**

(54) **REDOX FLOW BATTERIES BASED ON SUPPORTING SOLUTIONS CONTAINING CHLORIDE**

(75) Inventors: **Liyu Li**, Richland, WA (US); **Soowhan Kim**, Richland, WA (US); **Zhenguo Yang**, Richland, WA (US); **Wei Wang**, Richland, WA (US); **Jianlu Zhang**, Richland, WA (US); **Baowei Chen**, Richland, WA (US); **Zimin Nie**, Richland, WA (US); **Guanguang Xia**, Pasco, WA (US)

(73) Assignee: **Battelle Memorial Institute**, Richland, WA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 117 days.

(21) Appl. No.: **12/892,693**

(22) Filed: **Sep. 28, 2010**

(65) **Prior Publication Data**

US 2012/0077079 A1 Mar. 29, 2012

(51) **Int. Cl.**
H01M 6/04 (2006.01)

(52) **U.S. Cl.**
USPC **429/199**; 429/188; 429/200; 429/203

(58) **Field of Classification Search**
USPC 429/188, 199, 20, 203
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,996,064	A	12/1976	Thaller
4,469,760	A	9/1984	Giner
4,786,567	A	11/1988	Skyllas-Kazacos
4,814,241	A	3/1989	Nagashima
6,562,514	B1	5/2003	Kazacos et al.
7,320,844	B2	1/2008	Skyllas-Kazacos
2003/0143456	A1	7/2003	Kazacos et al.
2005/0244707	A1	11/2005	Skyllas-Kazacos et al.
2006/0183016	A1	8/2006	Kazacos et al.
2008/0292964	A1	11/2008	Kazacos

FOREIGN PATENT DOCUMENTS

JP	04019966	*	12/2007
JP	2010-086935	A	4/2010
WO	9512219	A1	5/1995
WO	9635239	A1	11/1996

OTHER PUBLICATIONS

JP-04019966 (proffesional translation).*
International Search Report/Written Opinion from International Application No. PCT/US2011/039626, International Filing Date Jun. 8, 2011, Date of Mailing Mar. 22, 2012.
Skyllas-Kazacos, Maria, "Novel vanadium chloride/polyhalide redox flow battery", Journal of Power Sources, 2003, 299-302 pps. vol. 124, Elsevier, Sydney, Australia.

(Continued)

Primary Examiner — Patrick Ryan
Assistant Examiner — Alex Usyatinsky
(74) *Attorney, Agent, or Firm* — Allen C. Tuan

(57) **ABSTRACT**

Redox flow battery systems having a supporting solution that contains Cl^- ions can exhibit improved performance and characteristics. Furthermore, a supporting solution having mixed SO_4^{2-} and Cl^- ions can provide increased energy density and improved stability and solubility of one or more of the ionic species in the catholyte and/or anolyte. According to one example, a vanadium-based redox flow battery system is characterized by an anolyte having V^{2+} and V^{3+} in a supporting solution and a catholyte having V^{4+} and V^{5+} in a supporting solution. The supporting solution can contain Cl^- ions or a mixture of SO_4^{2-} and Cl^- ions.

13 Claims, 11 Drawing Sheets