



(12) **United States Patent**
Shimizu et al.

(10) **Patent No.:** **US 9,411,081 B2**
(45) **Date of Patent:** **Aug. 9, 2016**

(54) **METHOD OF MANUFACTURING POLARIZING PLATE**
(75) Inventors: **Takashi Shimizu**, Ibaraki (JP); **Takashi Kamijo**, Ibaraki (JP); **Hitoshi Kitagishi**, Ibaraki (JP); **Minoru Miyatake**, Ibaraki (JP); **Shusaku Goto**, Ibaraki (JP); **Takeharu Kitagawa**, Ibaraki (JP); **Tomohiro Mori**, Ibaraki (JP); **Nobuyuki Haida**, Ibaraki (JP)

(73) Assignee: **NITO DENKO CORPORATION**, Osaka (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 496 days.

(21) Appl. No.: **13/991,278**

(22) PCT Filed: **Dec. 1, 2011**

(86) PCT No.: **PCT/JP2011/077820**
§ 371 (c)(1),
(2), (4) Date: **Jun. 3, 2013**

(87) PCT Pub. No.: **WO2012/074063**
PCT Pub. Date: **Jun. 7, 2012**

(65) **Prior Publication Data**
US 2013/0249129 A1 Sep. 26, 2013

(30) **Foreign Application Priority Data**
Dec. 2, 2010 (JP) 2010-269658
May 31, 2011 (JP) 2011-122663

(51) **Int. Cl.**
G02B 5/30 (2006.01)
B29C 55/04 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **G02B 5/30** (2013.01); **B29C 55/023** (2013.01); **B29C 55/04** (2013.01); **G02B 5/305** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC G02B 5/30; G02B 5/305; G02B 5/3041; B29C 55/02; B29C 55/023; B29C 55/026; B29C 55/04; B29C 55/06; B29C 55/065
USPC 264/1.24, 1.31, 1.34, 1.7, 2.7
See application file for complete search history.

(56) **References Cited**
U.S. PATENT DOCUMENTS

4,356,523 A 10/1982 Yeh
4,659,523 A 4/1987 Rogers et al.
(Continued)

FOREIGN PATENT DOCUMENTS

CN 101808806 B 1/2014
EP 2 405 288 A1 1/2012
(Continued)

OTHER PUBLICATIONS

International Search Report for PCT/JP2011/077820, mailing date of Feb. 28, 2012.
(Continued)

Primary Examiner — Alison L Hindenlang
Assistant Examiner — Lawrence D Hohenbrink, Jr.
(74) *Attorney, Agent, or Firm* — Westerman, Hattori, Daniels & Adrian, LLP

(57) **ABSTRACT**
The present invention provides a method of manufacturing a polarizing plate having sufficient heat resistance, without deteriorating the dye-affinity and the like of the polarizing film and without the necessity of transferring or detaching the polarizing film. Provided is a method of manufacturing a polarizing plate (10) that includes a polyester resin base (11) and a polarizing film including a polyvinyl alcohol resin laminated on the polyester resin base. The method includes the steps of: stretching a laminate that includes a polyvinyl alcohol resin layer (12) laminated on the polyester resin base (11); dyeing the polyvinyl alcohol resin layer (12); and crystallizing the polyester resin base (11). The crystallization step is performed after the dyeing step.

15 Claims, 1 Drawing Sheet

