



US009387082B2

(12) **United States Patent**  
**Myung et al.**

(10) **Patent No.:** **US 9,387,082 B2**  
(45) **Date of Patent:** **Jul. 12, 2016**

(54) **HYDROGEL ARTHROPLASTY DEVICE**

(71) Applicants: **The Board of Trustees of the Leland Stanford Junior University**, Stanford, CA (US); **The United States of America as Represented by the Department of Veterans Affairs**, Washington, DC (US)

(72) Inventors: **David Myung**, Santa Clara, CA (US); **Lampros Kourtis**, San Francisco, CA (US); **Laura Hartmann**, Berlin (DE); **Curtis W. Frank**, Cupertino, CA (US); **Stuart B. Goodman**, Los Altos, CA (US); **Dennis R. Carter**, Stanford, CA (US)

(73) Assignees: **The Board of Trustees of the Leland Stanford Junior University**, Palo Alto, CA (US); **The United States of America as Represented by the Department of Veterans Affairs**, Washington, DC (US)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/188,257**

(22) Filed: **Feb. 24, 2014**

(65) **Prior Publication Data**

US 2014/0172098 A1 Jun. 19, 2014

**Related U.S. Application Data**

(63) Continuation of application No. 13/418,294, filed on Mar. 12, 2012, now Pat. No. 8,679,190, which is a

(Continued)

(51) **Int. Cl.**

**A61F 2/30** (2006.01)

**A61F 2/38** (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC ..... **A61F 2/30756** (2013.01); **A61F 2/3872** (2013.01); **A61L 27/3843** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC ..... **A61F 2002/30075**; **A61F 2/30756**; **A61F 2/34**

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,030,327 A 4/1962 Hosch  
3,053,251 A 9/1962 Black et al.

(Continued)

FOREIGN PATENT DOCUMENTS

EP 1779875 A1 5/2007  
GB 2372707 A 9/2002

(Continued)

OTHER PUBLICATIONS

Bobyn et al., The optimum pore size for the fixation of porous-surfaced metal implants by the ingrowth of bone. Clin Orthop Relat Res, Jul./Aug. 1980(150): p. 263-70.

(Continued)

*Primary Examiner* — Michael A Salvitti

(74) *Attorney, Agent, or Firm* — Shay Glenn LLP

(57) **ABSTRACT**

An arthroplasty device is provided having an interpenetrating polymer network (IPN) hydrogel that is strain-hardened by swelling and adapted to be held in place in a joint by conforming to a bone geometry. The strain-hardened IPN hydrogel is based on two different networks: (1) a non-silicone network of preformed hydrophilic non-ionic telechelic macromonomers chemically cross-linked by polymerization of its end-groups, and (2) a non-silicone network of ionizable monomers. The second network was polymerized and chemically cross-linked in the presence of the first network and has formed physical cross-links with the first network. Within the IPN, the degree of chemical cross-linking in the second network is less than in the first network. An aqueous salt solution (neutral pH) is used to ionize and swell the second network. The swelling of the second network is constrained by the first network resulting in an increase in effective physical cross-links within the IPN.

**9 Claims, 29 Drawing Sheets**

