United States Patent [19]

Modic

[11] Patent Number: 4,500,584

[45] Date of Patent: Feb. 19, 1985

[54] TRANSPARENT MEMBRANE STRUCTURES

[75] Inventor: Frank J. Modic, Scotia, N.Y.

[73] Assignee: General Electric Company, Waterford, N.Y.

[21] Appl. No.: 511,704

[22] Filed: Jul. 7, 1983

[51] Int. Cl.[3] B32B 5/02

[52] U.S. Cl. 428/145; 427/387; 427/407.3; 427/412; 428/141; 428/143; 428/240; 428/241; 428/242; 428/244; 428/248; 428/251; 428/252; 428/253; 428/266; 428/273; 428/283; 428/285; 428/290; 428/333; 428/447; 428/448

[58] Field of Search 428/240, 241, 242, 244, 428/245, 251, 252, 253, 254, 266, 268, 273, 290, 391, 447, 448, 283, 285, 141, 143, 145, 248; 427/387, 407.3, 412

[56] References Cited

U.S. PATENT DOCUMENTS

3,284,406	11/1966	Nelson	260/46.5
3,436,366	4/1969	Modic	260/37
3,457,214	7/1969	Modic	260/37
3,527,655	9/1970	Ballard	117/72
3,639,155	2/1972	Harlein et al.	117/138.8
4,297,265	10/1981	Olsen	260/33.6 SB
4,300,532	11/1981	Olsen	126/417
4,358,558	11/1982	Shimizu	524/847

OTHER PUBLICATIONS

"Fabric Structures Taking Shape", Industrial Fabric Products Review, Nov. 1982, p. 28.

Primary Examiner—James J. Bell

Attorney, Agent, or Firm—Gary L. Loser

[57] ABSTRACT

A curable silicone coating composition which is resistant to dirt pickup, comprising:

(1) a vinyl chainstopped polysiloxane having a viscosity up to 2,000,000 centipoise;

(2) 1 to 2 parts of a resinous organopolysiloxane copolymer per part of (1);

(3) a platinum catalyst and,

(4) an organohydrogenpolysiloxane crosslinking agent.

42 Claims, No Drawings