US008882990B2

(12) **United States Patent**
Hallen et al.

(10) **Patent No.: US 8,882,990 B2**
(45) **Date of Patent: Nov. 11, 2014**

(54) **DEOXYGENATION OF FATTY ACIDS FOR PREPARATION OF HYDROCARBONS**

(75) Inventors: **Richard T. Hallen**, Richland, WA (US); **Karl O. Albrecht**, Richland, WA (US); **Heather M. Brown**, Kennewick, WA (US); **James F. White**, Richland, WA (US)

(73) Assignee: **Battelle Memorial Institute**, Richland, WA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 133 days.

(21) Appl. No.: **13/620,197**

(22) Filed: **Sep. 14, 2012**

(65) **Prior Publication Data**

US 2013/0018213 A1 Jan. 17, 2013

Related U.S. Application Data

(62) Division of application No. 12/848,887, filed on Aug. 2, 2010, now Pat. No. 8,366,907.

(51) **Int. Cl.**

C10M 101/00	(2006.01)
C10M 177/00	(2006.01)
C10G 71/00	(2006.01)
C10G 3/00	(2006.01)
B01J 23/62	(2006.01)
C11C 3/00	(2006.01)
C10L 1/12	(2006.01)
B01J 37/02	(2006.01)
B01J 21/18	(2006.01)
B01J 21/06	(2006.01)
B01J 23/652	(2006.01)
C10L 1/08	(2006.01)

(52) **U.S. Cl.**

CPC ***B01J 23/6525*** (2013.01); ***C10G 3/48*** (2013.01); ***B01J 23/626*** (2013.01); ***C11C 3/00*** (2013.01); *C10L 2200/0469* (2013.01); ***B01J 23/624*** (2013.01); *C10G 2400/04* (2013.01); ***C10L 1/1208*** (2013.01); ***B01J 37/0205*** (2013.01); ***B01J 21/18*** (2013.01); *C10G 2300/1014* (2013.01); *C10L 2270/02* (2013.01); ***B01J 21/066*** (2013.01); *C10G 2400/30* (2013.01); *C10G 2300/4081* (2013.01); *C10G 2300/4012* (2013.01); *C10G 2300/1018* (2013.01); ***B01J 37/0203*** (2013.01); *Y02T 50/678* (2013.01); ***C10L 1/08*** (2013.01); *C10G 2300/4018* (2013.01); *Y02E 50/13* (2013.01); *C10G 2400/08* (2013.01); ***C10G 3/47*** (2013.01); ***B01J 23/6527*** (2013.01); *C10G 2300/44* (2013.01); *C10L 2270/04* (2013.01); *C10G 2300/205* (2013.01); ***C10G 3/44*** (2013.01)

USPC **208/18**; 208/63; 585/734; 585/737

(58) **Field of Classification Search**

CPC C10L 2270/04; C10G 2300/205; C10G 3/44; C10G 3/48; B01J 23/626

USPC 208/18, 63; 585/734, 737

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,953,232	A	4/1934	Jaeger
1,964,516	A	6/1934	Jaeger
2,816,905	A	12/1957	Gilbert et al.
2,816,906	A	12/1957	Gilbert et al.
2,902,512	A	9/1959	Verheyden et al.
3,391,191	A	7/1968	Velde
3,476,803	A	11/1969	Pine
3,530,198	A	9/1970	Fenton
3,632,822	A	1/1972	Conroy
3,660,491	A	5/1972	Thigpen et al.
3,732,263	A	5/1973	Berman
3,856,876	A	12/1974	Burnett
3,962,035	A	6/1976	Antos
4,102,938	A	7/1978	Rao
4,262,157	A	4/1981	Hori et al.
4,303,486	A	12/1981	Bard et al.
4,320,241	A	3/1982	Frankiewicz
4,554,397	A	11/1985	Stern et al.
4,950,763	A	8/1990	Schommer et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CA	1201080	2/1986
EP	0478075	4/1992

(Continued)

OTHER PUBLICATIONS

Ai, M., "Activities for the decomposition of formic acid and the acid-base properties of metal oxide catalysts," *Journal of Catalysis*, 50, (2), 291-300, 1977.

Ai, M., "The activity of $W0_3$-based mixed-oxide catalysts: I. Acidic properties of WO_3-based catalysts and correlation with catalytic activity," *Journal of Catalysis*, 49, (3), 305-312, 1977.

Ai, M., "The oxidation activity and acid-base properties of SnO_2-based binary catalysts : I. The SnO_2—V_2O_5 system," *Journal of Catalysis*, 40, (3), 318-326, 1975.

Ai, M.; Ikawa, T., The acid-base properties of MoO_3—Bi_2O_3 —P_2O_5 catalysts and their correlation with catalytic activity and selectivity. *Journal of Catalysis*, 40, (2), 203-211, 1975.

Ai, M.; Suzuki, S., "Oxidation activity and acidity of MoO_3—P_2O_5 catalysts," *Journal of Catalysis*, 30, (3), 362-371, 1973.

Aizenshtat, Z.; Miloslaysky, I.; Heller-Kallai, L., "The effect of montmorillonite on the thermal decomposition of fatty acids under "bulk flow" conditions," *Organic Geochemistry* 7, (1), 85-90, 1984.

Alencar, J. W.; Alves, P. B.; Craveiro, A. A., "Pyrolysis of tropical vegetable oils," *Journal of Agricultural and Food Chemistry*, 31, (6), 1268-1270, 1983.

(Continued)

Primary Examiner — Shawquia Young

(74) *Attorney, Agent, or Firm* — Klarquist Sparkman, LLP

(57) **ABSTRACT**

Embodiments of methods for making renewable diesel by deoxygenating (decarboxylating/decarbonylating/dehydrating) fatty acids to produce hydrocarbons are disclosed. Fatty acids are exposed to a catalyst selected from a) Pt and MO_3 on ZrO_2 (M is W, Mo, or a combination thereof), or b) Pt/Ge or Pt/Sn on carbon, and the catalyst decarboxylates at least 10% of the fatty acids. In particular embodiments, the catalyst consists essentially of 0.7 wt % Pt and 12 wt % WO_3, relative to a mass of catalyst, or the catalyst consists essentially of a) 5 wt % Pt and b) 0.5 wt % Ge or 0.5 wt % Sn, relative to a mass of catalyst. Deoxygenation is performed without added hydrogen and at less than 100 psi. Disclosed embodiments of the catalysts deoxygenate at least 10% of fatty acids in a fatty acid feed, and remain capable of deoxygenating fatty acids for at least 200 minutes to more than 350 hours.

20 Claims, 31 Drawing Sheets