US006013694A

United States Patent [19]

Jia et al.

[11] **Patent Number: 6,013,694**

[45] **Date of Patent: Jan. 11, 2000**

[54] **DENTAL COMPOSITES COMPRISING GROUND, DENSIFIED, EMBRITTLED GLASS FIBER FILLER**

[75] Inventors: **Weitao Jia**, Wallingford; **Martin L. Schulman**, Orange; **Arun Prasad**, Cheshire; **Bruce Alpert**, Madison, all of Conn.

[73] Assignee: **Jeneric/Pentron Incorporated**, Wallingford, Conn.

[21] Appl. No.: **08/951,414**

[22] Filed: **Oct. 16, 1997**

[51] **Int. Cl.**[7] **C08K 3/40**; A61K 6/08

[52] **U.S. Cl.** **523/116**; 523/115; 524/450; 524/494; 501/69; 65/33.1; 65/33.7; 65/442

[58] **Field of Search** 523/115, 116; 501/69; 524/450, 494; 65/33.1, 33.7, 442

[56] **References Cited**

U.S. PATENT DOCUMENTS

2,477,268	7/1949	Saffir .	
2,514,076	7/1950	Kelly .	
3,096,144	7/1963	Wainer et al. .	
3,328,230	6/1967	Levecque et al. .	
4,215,033	7/1980	Bowen .	
4,381,918	5/1983	Ehrnford .	
4,392,828	7/1983	Ehrnford .	
4,427,799	1/1984	Orlowski et al. .	
4,500,657	2/1985	Kumar	523/117
4,514,174	4/1985	Dougherty et al. .	
4,707,504	11/1987	Walkowiak et al. .	
4,717,341	1/1988	Goldberg et al. .	
4,731,394	3/1988	Vogel et al. .	
4,744,759	5/1988	Bowen .	
4,793,809	12/1988	Sigler et al. .	
4,894,012	1/1990	Goldberg et al. .	
4,952,530	8/1990	Brosnan et al. .	
4,997,373	3/1991	Tanaka et al. .	
5,078,596	1/1992	Carberry et al. .	
5,081,164	1/1992	Lai .	
5,084,491	1/1992	Kerby .	
5,266,609	11/1993	Hall et al. .	
5,378,737	1/1995	Jacobs et al. .	
5,549,123	8/1996	Okuyama et al. .	
5,621,035	4/1997	Lyles et al. .	
5,676,745	10/1997	Kelly et al. .	
5,788,499	8/1998	Hoffman .	

FOREIGN PATENT DOCUMENTS

2 416 074	8/1979	France .

OTHER PUBLICATIONS

DentsplyCaulk, *Sure Fill, High Density Posterior Restorative, Technical Manual,* pp. 1–23.

K.F. Leinfelder et al, *A New Polymer Rigid Matrix Material,* CDA Journal, Sep. 1996, pp. 78–82.

Primary Examiner—Andrew E. C. Merriam
Attorney, Agent, or Firm—Cantor Colburn LLP

[57] **ABSTRACT**

A composite for a dental restoration is presented comprising ground, densified, embrittled glass fibers together with fillers and a polymeric matrix precursor composition. The ground, densified, embrittled glass fibers are obtained by grinding glass fibers which have been densified and embrittled by heating glass fibers at a temperature substantially below the softening point of the glass fibers, without significant fusion or melting together of the fibers. The composite is particularly useful as a direct filling material, in that it has the feel and workability of an amalgam.

48 Claims, 2 Drawing Sheets